



# Chemical Resistance Guide- Hybrid

## RATINGS KEY

R → Recommended	Little or no visible damage
RC → Recommended Conditional	Some Effect, swelling, discoloration
C → Conditional	Crackling-wash down within 1 hour of spillage to avoid effects
NR → Not Recommended	
Dis → Discoloration	

REAGENT	RATING	REAGENT	RATING
Acetic Acid (100%)	C	Phosphoric Acid (10%)	R
Acetone	C	Phosphoric Acid (50%)	NR
Ammonium Hydroxide (50%)	R	Potassium Hydroxide (10%)	R
Benzene	C	Potassium Hydroxide (20%)	R, Dis
Brine-Saturated H <sub>2</sub> O (310g/l)	R	Propylene Carbonate	RC
Chlorinated H <sub>2</sub> O	R	Skydrol®	C
Clorox® (10%) H <sub>2</sub> O	R	Sodium Hydroxide (25%)	R
Diesel Fuel	RC	Sodium Hydroxide (50%)	R
Gasoline	RC	Sodium Hypochlorite (10%)	R
Gasoline / 5% MTBE	RC	Sodium Bicarbonate	R
Gasoline / 5% Methanol	RC	Stearic Acid	R
Hydrochloric Acid (37%)	R	Sugar /H <sub>2</sub> O (5%)	R
Hydrofluoric Acid (10%)	NR	Sulfuric Acid (10%)	R
Hydraulic Fluid (oil)	RC	Sulfuric Acid (50%)	R
Isopropyl Alcohol	R	Toluene	R
Lactic Acid	RC	1,1,1-Trichlorethane	C
MEK	RC	Trisodium Phosphate	R
Methanol	R	Vinegar / H <sub>2</sub> O (5%)	R
Methylene Chloride	C	H <sub>2</sub> O	R
Mineral Spirits	RC	H <sub>2</sub> O (14 days @ 82°C)	R
Motor Oil	R	Xylene	RC
MTBE	C		
Muriatic Acid (10%)	R		
NaCl / H <sub>2</sub> O (10%)	R		
Nitric Acid (50%)	R		

October 2013

WARRANTY STATEMENT | IMPORTANT: The data on this sheet represent typical values, and since application variables are a major factor in product performance, this information should serve only as a general guide.

Xtreme Engineered Floor Systems assumes no obligation or liability for use of this information.